

**Product:**

**Advanced SL**



<b>Dry Adhesion (lbf/failure mode)</b>	
Aluminum	13.30/100c
Brick	12.08/100c
Concrete	13.73/100c
EPDM (Black or White)	7.68/100c
Galvanized Steel	13.28/100c
Glass	11.39/100c
Luan (Wood)	4.09/100a
PVC	10.01/100c
Steel	13.32/100c
Tile	13.84/100c
Vinyl	12.28/100c
Tensile at Peak (psi)	153
Elongation at Break (%)	304
Type "A" Hardness	36
Tack Free Time (ASTM method)	1 hr 25 min
Cure Rate by Weight Loss (Internal)	2 days
Product test date	11/14

Geocel Products Group  
A Business Unit of the Sherwin-Williams Company  
Cleveland, OH 44115

Questions?

Call Customer Service at 800-348-7615

Title:	EPDM Sealant Product Spec Template	Location:	W:\BMS Site Forms
Document Code:	EK - 2-63	Revision Number:	0
Issue Date:	5/21/2014	Page:	1 of 1
Author:	Plant Quality Manager	Approver:	Plant Quality Manager