



#C-10
Synthetic Rubber
FLOW SEAL
11 OZ. TUBE CAULK

CAUTION: NOT RECOMMENDED FOR EPDM RUBBER ROOFS

PRODUCT DESCRIPTION

#C-10 Flow Seal Sealant is formulated with Synthetic Rubber, which forms a tough, flexible, synthetic rubber seal.

RECOMMENDED USES Horizontal surfaces such as roofs on recreational vehicles, mobile homes, metal buildings, utility sheds, roofovers, vents, seams, carports, inside gutters, and many other uses!

PRODUCT ADVANTAGES

- * Self Leveling
- * Will not surface harden and crack
- * Flammability.....Self-extinguishing
- * Resists growth of mold, mildew, fungus, and bacteria
- * When cured, resists water, oil, grease, gasoline, salt solutions and many other chemicals
- * Paintable
- * Dries exceptionally fast
- * Extremely weather resistant

LIMITATIONS

#C-10 Flow Seal can be applied from 0° to 120° F., and in all types of weather conditions, but the surface must be clean and dry. Because this sealant flows from 2" to 1", allow that distance from the edge of the horizontal surface to prevent running over the side onto the vertical surface. If applied to a slightly pitched roof, allow at least 2" from the edge of the horizontal surface to prevent run over.

CAUTION

FLAMMABLE: Contains Xylene, toluene and petroleum distillates. Avoid contact with eyes and prolonged contact with skin. Use only in a well ventilated area. Do not use near heat, sparks, or flame.

LIMITATION OF LIABILITY

Technical data is true and accurate at date of issuance, but subject to change without notice. Our products conform to **DYCO** quality standards, but no other warranty or guarantee is expressed or implied. Liability, if any, is limited to replacement of product or purchase price. Labor, cost of labor, or other consequential damages is hereby excluded.

TECHNICAL DATA

Product Number - #C-10

Generic Type – Synthetic Rubber

Colors – White, Ivory and Grey

Sheen - Semi Gloss

% Solids by Weight – 54.08%
% Solids by Volume – 47.06%
% Vehicle Solids by Wt – 43.52%
% Pigment by Weight – 10.55%
% Solvents by Weight – 45.92%

Viscosity - Thick
Weight/Gallon - 8.26
Flash Point - 53° F.

Dry Time - 70° F., 50% R. H.
Touch - 30 to 60 minutes
Recoat - 24 hours

Clean Up Solvent - Xylene