

Product:

Proflex RV



Dry Adhesion (lbf/failure mode)	Clear	White	Bright White
Aluminum	17.98/100c	15.79/100c	15.88/100c
Brick	20.06/100c	17.75/100c	16.89/100c
Concrete	20.76/100c	18.57/100c	22.19/100c
Galvanized Steel	18.60/100c	16.59/100c	17.52/100c
Glass	19.87/100c	13.30/100c	19.10/100c
Kynar	20.27/100c	16.06/100c	18.51/100c
Luan	18.92/100c	19.03/95c	18.51/100c
Steel	19.52/100c	14.51/100c	17.61/100c
Tile	21.04/100c	16.45/100c	21.16/100c
Vinyl	18.42/100c	14.12/100c	15.70/100c
Tensile at Peak (psi)	96	99	85
Elongation at Break (%)	461	499	430
Type "A" Hardness	45	37	45
Tack Free Time (ASTM method)	70 mins	160 mins	45 mins
Cure Rate by Weight Loss (Internal)	3 days	6 days	3 days
Product test date	07/12	08/11	02/12

Geocel Products Group
A Business Unit of the Sherwin-Williams Company
Cleveland, OH 44115

Questions?

Call Customer Service at 800-348-7615

Title:	MHRV Product Spec Template	Location:	W:\BMS Site Forms
Document Code:	EK - 2-54	Revision Number:	0
Issue Date:	5/5/2014	Page:	1 of 1
Author:	Plant Quality Manager	Approver:	Plant Quality Manager